MetaGuard MGC

Cast Wrap Film Overlaminate (Matched with MDC)



Product Description

MetaGuard MGC Premium Cast Overlaminate provides a complete kit with MetaCast[®] Wrap films. The superior 40 micron matched film is available in a high Gloss, or low lustre Matt finish. The MetaCast wrap system offers the ultimate professional performance for Full Vehicle Wraps and backed by the MetaSure 10 year warranty. MetaGuard MGC has a layflat PE liner for trouble free handling.

Features

- Matched to MetaCast[®] Print films.
- 40 micron engineered film.
- Premium Cast Overlaminate for 3D wraps, deep channels & recesses.

Benefits

- 10 year durability and MetaSure Warranty.
- Highly conformable and ease of application.
- Engineered to give long term dimensional stability and provide durability to the print.

Face Film		Finishes	
Face Film Gauge (ISO 2286-3) Elongation at break	Cast Vinyl 40 micron nominal 190% MD nominal	Finishes Available	MGC-005 Gloss MGC-002 Matt
Adhesive		Roll Presentation	
Type Adhesion to glass 20 mins Adhesion to glass 24 hour	Permanent Solvent-Based Adhesive. 13N/25mm nominal 16N/25mm nominal +5°C to +40°C -30°C to +110°C	Roll Widths Roll Lengths	1.37m / 1.60m 50m / 25m
		Durability	
Application temperature Service temperature		Shelf Life External weathering	2 years. (10-20°C and 50% R.H). 10 years. Northern European conditions,
Release Liner		Ū	vertical. Refer to full Metamark
Print Weight Type	Metamark print 140 gsm nominal PE layflat	Fire Rating Chemical Resistance	International durability guide. Self-extinguishing. Unprinted film resistant to mild acids, aliphatic solvents, salt and alkali, diesel, gasoline, paraffin, hydraulic oil, antifreeze.
 Handling and Application This product is suitable for cold lamination using a laminator. Ensure that the material has reached room temperature and a 		 Suitable for use on Solvent, UV and Latex prints. The product is matched to MetaCast[®]. Matched laminates 	
 relative humidity of 50% before use. Allow the inks to cure before overlaminating, this is usually 24-48 hours. (Not applicable to HP Latex prints). Failure to do so can 		prevent tunnelling and delamination.Apply around 30°C on the top roller to prevent silvering of the adhesive.	
cause delamination, tunnelling and shrinkage.The matched laminate for MDC is MetaGuard MGC.		 Refer to www.metamark.co.uk for further application guideline The user should determine suitability of the overlaminate to th 	

 The user should determine suitability of the overlaminate to the print media

MetaSure® Warranty

Metamark (UK) Limited warrants to its customers that graphics produced using Metamark Media and Overlaminates will remain in good condition without excessive fading or colour degradation for the specified life time of the ink used, when correctly stored, printed and applied in accordance with procedures outlined in the technical literature. If within the specified years of normal use Metamark Media and Overlaminates becomes ineffective for its intended use, then Metamark will provide sufficient material to produce a new replacement marking, and will at its own discretion, contribute an allowance in additional material towards the costs involved in replacing the graphics. In all cases, the converter is held fully responsible for storing, processing and applying the unconverted materials in accordance with Metamark's technical specifications. Metamark (UK) Limited will not be liable for any indirect or consequential loss or damage, and will not provide any allowance against improper usage, application accident, negligence, chemical damage or improper repair. The above data is given in good faith to provide an indication of the performance of the product. Purchasers should consider the suitability of each product for its intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential loss.



Metamark (UK) Limited

Luneside • New Quay Road • Lancaster • LA1 5QP • Tel +44 (0)1524 387140 • Fax +44 (0)1524 387147
 Metamark House • Octimum Business Park • Forsyth Road • Woking • GU21 5SF • Tel +44 (0)1483 571111 • Fax +44 (0)1483 570!

Arkeneel 27 3905 NS Veenendaal